

BUNA[®] EP T 2070 P**Product Description**

Ethylene-propylene-rubber (EPM), low molecular weight, curable only by peroxide

Supply Form

Pellets

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+8) 100°C	36 ± 6	MU	ISO 289/ASTM D 1646
Ethylene content	68 ± 3	wt %	ASTM D 3900
Volatile matter	≤ 0.75	wt %	ASTM D 5668

Other Product Features

Property	Typical Value
Specific gravity	0.86 g/cm ³
Total Ash	≤ 0.5 wt % ASTM D 5667
Stabilizer	Non-staining

BUNA[®] EP T 2070 P

Packaging	pallets in liner bulk box (454 kg)
Shelf-life	24 month from date of production at temperatures not exceeding 30 °C in dry conditions; exposure to light has to be avoided.
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet no.823957.

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

BUNA[®] EP (EPM/EPDM) is a Registered Trademark of Bayer AG, Germany

Issue number: LX 02 / Date of issue: March 18, 2005 / Previous issue from 06.12.2004

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.